

Palayesh-e Hesar Mehran Co.

Brand: Hesar Mehran

Bitumen **160-220**



Penetration-Graded Asphalt Cement BS EN 12591		Test / Method			Grade 160-220	
		ASTM	AASHTO	INSO	Min	Max
		-	-	12505-1		
1	Softening Point , ⁰ C	D36	-	3868	35	43
2	Flash Point , ⁰ C	D92	T48	198	220	-
3	Penetration @ 25 ⁰ C , 0.1 mm	D5	T49	2950	160	220
4	Solubility in trichloroethylene , w %	D2042	T44	2953	99.00	-
5	Special Weight@ 25 ⁰ C , gr/cm ³	EN 12592	T228	3872	To be reported	
6	Rolling Thin-Film Oven Test	D2872	T240	11898	-	
6-1	Change in Mass ,w%	EN 12607-1			1 ≥	
6-2	Penetration,%				37 ≤	
6-3	Increase the softness point under normal conditions, ⁰ C OR Increase the softness point than usual, ⁰ C				11 ≥ Or 12 ≥	
6-4	Permeability index				NR -1.5 to +0.7	
6-5	Fraass breaking Point , ⁰ C				-	-



Address: South Ninth St, 60 meters Shurabad Blvd -Qom Old Road– Tehran – IRAN

www.hesarmehran.com

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326