

# Palayesh-e Hesar Mehran Co.



Brand: Hesar Mehran

Emulsion Bitumen **CRS-1**

Cationic Emulsified Asphalt		Test / Method		Acceptable range	
		ASTM	INSO	min	max
		D2397	12505-7		
1	Viscosity by Saybolt Furol Viscometer@ 50 °C,SFS	D7496	20644	20	100
2	Storage Stability@ 24hr,%	D6930	20637	—	1
3	Demulsibility of Emulsified Bitumen with 35 ml of aqueous solution of 0.8% sodium acetate and sulfosuccinate,%	D6936	13582	40	—
4	Determine the particle load	D7402	20642	Positive	
5	Sieve Test,%	D6933	20638	-	0.1
6	Distillation				
6-1	The oily product obtained from distillation relative to the volume of emulsion	D6997	13580	-	3
6-2	distillation residue,%			60	-
7	Test on distillation residue				
7-1	Penetration @ 25 °C ( 100 gr. 5s ),10 <sup>-1</sup> mm	D5	2950	100	250
7-2	Ductility @ 25 °C (5 cm/min ), Cm	D113	3866	40	-
7-3	Solubility in trichloroethylene, wt%	D7553	2953	97.5	-



6678520988

Address: South Ninth St , 60 meters Shurabad Blvd- Qom Old Road– Tehran – IRAN

[www.hesarmehran.com](http://www.hesarmehran.com)

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326