

Palayesh-e Hesar Mehran Co.

Brand: Hesar Mehran



Bitumen AC-10

No.	Test	Test / Method			Grade AC-10	
		ASTM	AASHTO	INSO	Min	Max
1	Viscosity @ 60°C,Pa.s	D2171	T202	12851	100±20	
2	Kinematic Viscosity @ 135°C,mm ² /s	D2170	-	12855	250	-
3	Penetration @ 25 °C,10 ⁻¹ mm	D5	T49	2950	80	-
4	Solubility in trichloroethylene ,wt%	D2042	T44	2953	99	-
5	Flash point ,°C	D92	T48	198	220	-
6	Special Weight@ 25°C	D70-03	T228	3872	To be reported	
7	Permibility index	EN 12607-1	-	-	-1.5	+1
8	Thin-Film Oven Test	D1754	T179	2957		
8-1	Viscosity @ 60°C,Pa.s	D2171	-	12851	-	500
8-2	Ductility @ 25 °C,Cm	D113	T51	3866	75	-
9	Spot Test	-	T102	2949	Negative	



Address: South Ninth St, 60 meters Shurabad Blvd -Qom Old Road– Tehran – IRAN

www.hesarmehran.com

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326