

Palayesh-e Hesar Mehran Co.



Brand: Hesar Mehran

Emulsion Bitumen / CMS-2

No.	Test	Test / Method		Acceptable range	
		ASTM	INSO	min	max
1	Viscosity by Saybolt Furol Viscometer@ 50 °C,SFS	D7496	20644	50	450
2	Storage Stability@ 24hr,%	D6930	20637	–	1
3	Evaluating Aggregate Coating and water resistance				
3-1	Coating ,dry Aggregate	D244	20640	good	–
3-2	Coating ,after spraying water			Average	–
3-3	Coating , wet Aggregate			Average	–
3-4	Coating ,after spraying water			Average	–
5	Determine the particle load	D7402	20642	Positive	
6	Sieve Test,%	D6933	20638	-	0.1
7	Distillation				
7-1	The oily product obtained from distillation relative to the volume of emulsion,%	D6997	13580	-	12
7-2	distillation residue,%			65	-
8	Test on distillation residue				
8-1	Penetration @ 25 °C (100 gr. 5s),10 ⁻¹ mm	D5	2950	100	250
8-2	Ductility @ 25 °C (5 cm/min), Cm	D113	3866	40	-
8-3	Solubility in trichloroethylene, wt%	D7553	2953	97.5	-



Address: South Ninth St , 60 meters Shurabad Blvd- Qom Old Road– Tehran – IRAN

www.hesarmehran.com

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326