

Palayesh-e Hesar Mehran Co.

Brand: Hesar Mehran

Bitumen MC-70



No.	Test	Test / Method		Grade MC-70		
		ASTM	ISIRI	Min	Max	
1	Kinematic Viscosity @ 60 °C, mm ² /s	D2171	12855	70	140	
2	Flash point(Tag open cup) ,°C	D3143	12860	38	-	
3	Water content	D95	-	-	0.2	
4	Spot Test	-	2949	Negative		
5	Distillation					
	Vol % of total distillate to 360 ⁰ C					
	5-1	To 225 °C, %	D402	12859	-	25
	5-2	To 260 °C, %			10	70
	5-3	To 316 °C, %			65	93
5-4	Residue from distillation To 360 °C, %	55			-	
6	Test on residue from distillation:					
6-1	Ductility @ 25 °C,Cm	D113	3866	100	-	
6-2	Solubility , %	D2042	2953	99	-	
6-3	Kinematic Viscosity @ 60 °C, Pa.s	D2170	12851	30	120	



Address: South Ninth St ,60 meters shurabad Blvd - Qom Old Road– Tehran – IRAN

www.hesarmehran.com

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326