

Palayesh-e Hesar Mehran Co.



Brand: Hesar Mehran

Bitumen **20-30**

Penetration-Graded Asphalt Cement BS EN 12591		Test / Method			Grade 20-30	
		ASTM	AASHTO	INSO	Min	Max
		-	-	12505-1		
1	Softening Point , ⁰ C	D36	-	3868	55	63
2	Flash Point , ⁰ C	D92	T48	198	240	-
3	Penetration @ 25 ⁰ C , 0.1 mm	D5	T49	2950	20	30
4	Solubility in trichloroethylene , w %	D2042	T44	2953	99.00	-
5	Special Weight@ 25 ⁰ C , gr/cm ³	EN 12592	T228	3872	To be reported	
6	Rolling Thin-Film Oven Test	D2872	T240	11898	-	
6-1	Change in Mass , w %	EN 12607-1			0.5 ≥	
6-2	Penetration , %				55 ≤	
6-3	Increase the softness point under normal conditions, ⁰ C				8 ≥ Or 10 ≥	
	OR Increase the softness point than usual, ⁰ C					
6-4	Permeability index				NR -1.5 to +0.7	
6-5	Fraass breaking Point , ⁰ C	-	-	3867	NR	



Address: South Ninth St, 60 meters Shurabad Blvd -Qom Old Road– Tehran – IRAN

www.hesarmehran.com

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326