

Palayesh-e Hesar Mehran Co.

Brand: Hesar Mehran

Bitumen **60-70**



Penetration-Graded Asphalt Cement		Test / method			Grade 60-70	
		ASTM	AASHTO	INSO	Min	Max
		D946	-	12505-1		
1	Softening point , ⁰ C	D36	-	3868	46	-
2	Flash point , ⁰ C	D92	T48	198	230	-
3	Penetration @ 25 ⁰ C , 0.1 mm	D5	T49	2950	60	70
4	Solubility in trichloroethylene , w %	D2042	T44	2953	99	-
5	Ductility @ 25 ⁰ C , Cm	D113	T51	3866	100	-
6	Thin-Film Oven Test	D1754	T179	2957		
6-1	Change in Mass , w%	D1754	T179	2957	-	0.8
6-2	Retained Penetration @ 25 ⁰ C ,% of original	D1754/D5	T49	2950	52	-
6-3	Ductility of Residue @ 25 ⁰ C ,Cm	D1754/D113	T51	3866	50	-
7	Special Weight@ 25 ⁰ C , gr/cm ³	D70-03	T228	3872	To be reported	
8	Spot Test	-	T102	2949	Negative	



Address: South Ninth St, 60 meters Shurabad Blvd -Qom Old Road- Tehran – IRAN

www.hesarmehran.com

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326