

Palayesh-e Hesar Mehran Co.



Brand: Hesar Mehran

Bitumen PG 58-xx											Test Method	Unit	Test
PG - 64						PG - 58					D6373	-	Degree of performance
-40	-34	-28	-22	-16	-10	-40	-34	-28	-22	-16			
64>						58>					-	(°C)	Highest Pavement Temperature (The average 7 days)
-40<	-34<	-28<	-22<	-16<	-10<	-40<	-34<	-28<	-22<	-16<	-	(°C)	Lowest Pavement Temperature
Bitumen before aging													
Min 230											INSO 198	(°C)	Flash point
max 3											ASTM D4402	@ 135°C · Pa.S	Rotational viscosity (RV)
64						58					ASTM D7175	Test temperature. (°C)	Dynamic Shear Rheometer (DSR)
-						min 1						G* / sinδ · KPa	
Rolling Thin-Film Oven Test (RTFOT)													
max 1											INSO 11898	%	Weight change
64						58					ASTM D7175	Test temperature. (°C)	Dynamic Shear Rheometer (DSR)
-						min 2.2						G* / sinδ · KPa	
Pressurized Aging Vessel (PAV)													
100											ASTM D6521	(°C)	Aging temperature
16	19	22	25	28	31	13	16	19	22	25	ASTM D7175	Test temperature. (°C)	Dynamic Shear Rheometer (DSR)
-						max 5000						G* · sinδ · KPa	
-30	-24	-18	-12	-6	0	-30	-24	-18	-12	-6	ASTM D6648	Test temperature. (°C)	Bending Beam Rheometer (BBR)
-						max 300						S@ 60 s, MPa	
-						min (0.3)						m	



Address: South Ninth St, 60 meters Shurabad Blvd -Qom Old Road- Tehran – IRAN

Tel :+982156546681 / Fax : +982156544326

mail: info@hesarmehran.com

Website: www.hesarmehran.com