



# Palayesh-e Hesar Mehran Product Data Sheet



Cutback Asphalt RC-250, (Rapid Curing Type)

Date:12/25/2024

Rev:01

Specification, Unit	Test Method			Min	Max
	ASTM D2028	AASHTO M81	INSO 12505-6		
Kinematic Viscosity at 60 °C, mm <sup>2</sup> /s	D2170	T201	12855	250	500
Flash point (Tag open-cup), °C	D3143	T79	12860	27	-
Water content, % Wt	D95	T55	4081	-	0.2
Spot Test	-	T102	2949	Negative	
Distillation Test					
Distillation, volume percent of total distillate to 360 °C					
to 190 °C, % Vol				-	-
to 225 °C, % Vol	D402	T78	12859	35	-
to 260 °C, % Vol				60	-
to 316 °C, % Vol				80	-
Residue from distillation to 360 °C, % Vol	D402	T78	12859	65	-
Test on Residue from Distillation					
Ductility at 25 °C, cm	D113	T51	3866	100	-
Solubility in trichloroethylene, % Wt	D2042	T44	2953	99.0	-
Viscosity at 60 °C, Pa.s	D2171	T202	12851	60	240

*Note: For latest version please contact us.*

Address: South Ninth St , 60 meters Shurabad Blvd- Qom  
Old Road- Tehran – IRAN

[www.hesarmehran.com](http://www.hesarmehran.com)

[info@hesarmehran.com](mailto:info@hesarmehran.com)

Tel :+982156546681

Fax : +982156544326