



Standard Specification for Cutback Asphalt (Rapid-Curing Type)¹

This standard is issued under the fixed designation D 2028; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers cutback petroleum asphalts of the rapid-curing type for use in the construction and treatment of pavements.

2. Referenced Documents

2.1 ASTM Standards:²

- D 5 Test Method for Penetration of Bituminous Materials
- D 95 Test Method for Water in Petroleum Products and Bituminous Materials by Distillation
- D 113 Test Method for Ductility of Bituminous Materials
- D 140 Practice for Sampling Bituminous Materials
- D 402 Test Method for Distillation of Cut-Back Asphaltic (Bituminous) Products
- D 2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.40 on Asphalt Specifications.

Current edition approved March 1, 2004. Published March 2004. Originally approved in 1963. Last previous edition approved in 1997 as D 2028-97.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D 2170 Test Method for Kinematic Viscosity of Asphalts (Bitumens)

D 3143 Test Method for Flash Point of Cutback Asphalt with Tag Open-Cup Apparatus

3. Properties

3.1 The cutback asphalt shall not foam when heated to application temperature and shall conform to the requirements prescribed in Table 1.

4. Test Methods

4.1 The material shall be sampled in accordance with Practice D 140, and the properties enumerated in this specification shall be determined in accordance with the following ASTM methods:

- 4.1.1 *Flash Point (Tag Open-Cup)*—Test Method D 3143.
- 4.1.2 *Viscosity, Kinematic*—Test Method D 2170.
- 4.1.3 *Distillation*—Test Method D 402.

NOTE 1—If a 100-mL graduate does not permit sufficiently close readings to determine conformity to these specifications with the desired accuracy, receivers graduated in 0.1-mL divisions shall be used.

- 4.1.4 *Penetration*—Test Method D 5.
- 4.1.5 *Ductility*—Test Method D 113.
- 4.1.6 *Solubility in Trichloroethylene*—Test Method D 2042.
- 4.1.7 *Water*—Test Method D 95.

TABLE 1 Requirements for Cutback Asphalt (Rapid-Curing Type)

NOTE—If the ductility at 25°C (77°F) is less than 100, the material will be acceptable if its ductility at 15°C (59°F) is more than 100.

Designation	RC-70		RC-250		RC-800		RC-3000	
	Min	Max	Min	Max	Min	Max	Min	Max
Kinematic viscosity at 60°C (140°F), mm ² s	70	140	250	500	800	1600	3000	6000
Flash point (Tag open-cup), °C (°F)	27 + (80 +)	...	27 + (80 +)	...	27 + (80 +)	...
Distillation test:								
Distillate, volume percent of total distillate to 360°C (680°F):								
to 190°C (374°F)	10
to 225°C (437°F)	50	...	35	...	15
to 260°C (500°F)	70	...	60	...	45	...	25	...
to 316°C (600°F)	85	...	80	...	75	...	70	...
Residue from distillation to 360°C (680°F), percent volume by difference	55	...	65	...	75	...	80	...
Tests on residue from distillation:								
Viscosity at 60°C (140°F), Pa · s ^A	60	240	60	240	60	240	60	240
Ductility at 25°C (77°F), cm	100	...	100	...	100	...	100	...
Solubility in trichloroethylene, %	99.0	...	99.0	...	99.0	...	99.0	...
Water, %	...	0.2	...	0.2	...	0.2	...	0.2

^A Instead of viscosity of the residue, the specifying agency, at its option, can specify penetration at 100 g: 5 s at 25°C (77°F) of 80 to 120 for Grades RC-70, RC-250, RC-800, and RC-3000. However, in no case will both be required.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).