



Palayesh-e Hesar Mehran Product Data Sheet



Penetration-Graded Asphalt Cement for Use in Pavement Construction
Bitumen 85-100

Date:12/25/2024
Rev:01

Specification, Unit	Test Method			Min	Max
	ASTM D946	AASHTO	INSO 12505-1		
Softening point, °C	D36	T53	3868	42	-
Flash point, °C	D92	T48	198	230	-
Penetration @ 25°C 100g, 5s, 0.1 mm	D5	T49	2950	85	100
Solubility in trichloroethylene, %	D2042	T44	2953	99	-
Ductility @ 25°C, cm	D113	T51	3866	100	-
Special weight @ 25°C, g/cm³	D70	T228	3872	To be reported	
Spot Test	-	T102	2949	Negative	
Thin-Film Oven Test					
Change of Mass after Heating, %	D1754	T179	2957	-	1
Retained Penetration @ 25°C, % of original	D1754/D5	T49	2950	47	-
Ductility of Residue @ 25°C, cm	D1754/D113	T51	3866	75	-

Note: For latest version please contact us.

Address: South Ninth St , 60 meters Shurabad Blvd- Qom
Old Road- Tehran – IRAN

www.hesarmehran.com

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326