



# Palayesh-e Hesar Mehran Product Data Sheet



Date:12/25/2024

Sealant Mastic Type I

Rev:01

Specification, Unit	Test Method		Min	Max
	ASTM D6690	INSO 23397		
Conte Penetration at 25°C, 0.1 mm	D5329	12600	-	90
Softening point, °C	D36	3868	80	-
Bond, non-immersed	D5329	12600	Two out of three 12.5±0.4mm specimens pass 5 cycles at 50% ext. at -18 °C	
Bond, water immersed	D5329	12600	-	
Resilience, %	D5329	12600	-	-
Oven Aged Resilience, %	D5329	12600	-	-
Asphalt Compatibility	D5329	12600	Pass	

*Note: For latest version please contact us.*

Address: South Ninth St , 60 meters Shurabad Blvd- Qom Old Road- Tehran – IRAN

[www.hesarmehran.com](http://www.hesarmehran.com)

[info@hesarmehran.com](mailto:info@hesarmehran.com)

Tel :+982156546681

Fax : +982156544326