



Palayesh-e Hesar Mehran Product Data Sheet



Date:12/25/2024

Sealant Mastic Type II

Rev:01

| Specification, Unit | Test Method | | Min | Max |
|-----------------------------------|---------------|---------------|---|-----|
| | ASTM D6690 | INSO 23397 | | |
| Conte Penetration at 25°C, 0.1 mm | D5329 | 12600 | - | 90 |
| Softening point, °C | D36 | 3868 | 80 | - |
| Bond, non-immersed | D5329 | 12600 | Three 12.5±0.2mm specimens pass 3 cycles at 50% ext. at -29 °C | |
| Bond, water immersed | D5329 | 12600 | - | |
| Resilience, % | D5329 | 12600 | 60 | - |
| Oven Aged Resilience, % | D5329 | 12600 | - | - |
| Asphalt Compatibility | D5329 | 12600 | Pass | |

Note: For latest version please contact us.

Address: South Ninth St , 60 meters Shurabad Blvd- Qom Old Road- Tehran – IRAN

www.hesarmehran.com

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326