



Palayesh-e Hesar Mehran Product Data Sheet



Date:12/25/2024

Sealant Mastic Type III

Rev:01

Specification, Unit	Test Method		Min	Max
	ASTM D6690	INSO 23397		
Conte Penetration at 25°C, 0.1 mm	D5329	12600	-	90
Softening point, °C	D36	3868	80	-
Bond, non-immersed	D5329	12600	Three 12.5±0.2mm specimens pass 3 cycles at 50% ext. at -29 °C	
Bond, water immersed	D5329	12600	Three 12.5±0.2mm specimens pass 3 cycles at 50% ext. at -29 °C	
Resilience, %	D5329	12600	60	-
Oven Aged Resilience, %	D5329	12600	60	-
Asphalt Compatibility	D5329	12600	Pass	

Note: For latest version please contact us.

Address: South Ninth St , 60 meters Shurabad Blvd- Qom Old Road- Tehran – IRAN

www.hesarmehran.com

info@hesarmehran.com

Tel :+982156546681

Fax : +982156544326

F137/00(403.10.06)